**1512 BATAVIA AVENUE ENEVA, ILLINOIS 60134** 

#### OF **IIT RESEARCH INSTITUTE**

REFORT

630/232-0104 **FOUNDED 1918 BY WALLACE CLEMENT SABINE** 

FOR: Auralex™ Acoustics

Sound Absorption Test

RAL™-A97-48

Page 1 of 4

ON:

4" Studiofoam Pyramids

CONDUCTED: 18 March 1997

#### TEST METHOD

The test method conformed explicitly with the requirements of the ASTM Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method: ASTM C423-90a and E795-92. Riverbank Acoustical Laboratories has been accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) for this test procedure. A description of the measuring technique is available separately. The microphone used was a Bruel & Kjaer serial number 1330828.

#### DESCRIPTION OF THE SPECIMEN

The test specimen was designated by the manufacturer as 4" Studiofoam pyramids. The overall dimensions of the specimen as measured were 2.44 m (96 in.) wide by 2.44 m (96 in.) high and 102 mm (4 in.) thick. The specimen consisted of eight units that measured 610 mm (24 in.) wide by 1.22 m (48 in.) long and 102 mm (4 in.) thick. The specimen was tested in the laboratory's 292 m3 (10,311 ft3) test chamber. The manufacturer's description of the specimen was as follows: The 4" Studiofoam was a 102 mm (4 in.) thick, pyramid cut, open cell, polyurethane foam with a 25 mm (1 in.) base, and a 76 mm (3 in.) pyramid height. A visual inspection verified the manufacturer's description of the specimen. The weight of the specimen as measured was 8.2 kg (18 lbs) an average of 1.37 kg/m $^2$  (0.28 lbs/ft $^2$ ). The area used in the calculations was 6.0 m $^2$  (64 ft $^2$ ). The room temperature at the time of the test was 21°C (70°F) and 62% relative humidity.

#### MOUNTING A

The test specimen was laid directly against the test surface.

OR IMPLIES PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY NIST.

**1512 BATAVIA AVENUE INEVA, ILLINOIS 60134** 

# **IIT RESEARCH INSTITUTE**

630/232-0104 **FOUNDED 1918 BY** WALLACE CLEMENT SABINE

Auralex™ Acoustics

RAL - A97-48

18 March 1997

Page 2 of 4

### TEST RESULTS

1/3 Octave Center Center Frequency (Hz)	Absorption Coefficient	Total Absorption In Sabins	% Of Uncertainty With 95% Confidence Limit With Specimen
100	0.21	13.71	3.20
** 125	0.27	17.30	2.78
160	0.28	17.88	2.54
200	0.37	23.42	1.75
** 250	0.50	32.02	1.59
315	0.70	45.05	1.27
400	0.85	54.31	1.49
** 500	1.01	64.34	1.22
630	1.09	69.85	0.97
800	1.13	72.08	0.87
** 1000	1.13	72.52	0.81
1250	1.13	72.19	0.77
1600	1.12	71.37	0.62
** 2000	1.11	71.10	0.60
2500	1.12	71.66	0.63
3150	1.09	69.95	0.49
** 4000	1.12	71.51	0.50
5000	1.13	72.58	0.54

NRC = 0.95

THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES OR IMPLIES PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY NIST.

**1512 BATAVIA AVENUE INEVA. ILLINOIS 60134** 

#### OF **IIT RESEARCH INSTITUTE**

KEFORT

630/232-0104 **FOUNDED 1918 BY** WALLACE CLEMENT SABINE

Auralex™ Acoustics

RAL™-A97-48

18 March 1997

Page 3 of 4

# TEST RESULTS (con't)

The percentage of uncertainty for the required 95% confidence limits indicated above must fall within the prescribed limits designated in par. 13.2 of ASTM C423-90a. It states that for the absorption of the reverberation room containing the specimen the testing laboratory shall obtain data with less than 4% uncertainty at 125 (hertz) and 2% uncertainty at 250, 500, 1000, 2000, and 4000 (hertz). The method of calculation is described in ASTM STP 15D and outlined in section 13 of the standard.

Tested & Reviewed by

Dean Victor

Senior Experimentalist

Submitted by

Peter E.

Senior Experimentalist

OR IMPLIES PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY NIST.


**1512 BATAVIA AVENUE INEVA, ILLINOIS 60134** 

#### OF **IIT RESEARCH INSTITUTE**

630/232-0104 **FOUNDED 1918 BY WALLACE CLEMENT SABINE** 

REPORT





NRC = 0.95